

weber.color classic



Category	Normal cementitious tile grout	
Composition	White cement, Special aggregates, Special additives, Synthetic resins, Organics & Inorganics pigments.	
Performance	Suitable for tile joint width from 1-6 mm. Resistant to usual cleaning powders & liquids Non abrasive materials	
International standard (ISO 13007) and European Norms (EN 12004 : 2001) test methods	Standard	Result
Working time or Pot life*	-	30 minutes
Density of dry mortar*	-	0.9 - 1.1
Flexural strength ISO 13007 part 4-4.1.3 or EN 12808-3	$\geq 3.5 \text{ N/mm}^2 \text{ (MPa)}$	4.68 N/mm^2
Compressive strength ISO 13007 part 4-4.1.4 or EN 12808-3	$\geq 15 \text{ N/mm}^2 \text{ (MPa)}$	26.94 N/mm^2
Shrinkage ISO 13007 part 4-4.1.4 or EN 12808-4	$\leq 2 \text{ mm./m.}$	1.11 N/mm^2
Color	24 colors (see color chart)	
Exposure	Internal walls & floors External floors External walls $\leq 8 \text{ m.}$	

* at temp. = 25 - 30 °C and on site requirement