

weber.color HR



Category	High resistance grout (2-10 mm.)
Composition	Special cement, Silica sands, Polymers, Water repellent, Specific admixtures, Specific additives
Performance	Conforms to EN12004:2001
European Norms test methods	EN12808-2, EN12808-3, EN12808-4, EN12808-5
Acid resistance	pH>3
Working time or Pot life*	30-40 minutes
Temperature resistance	-40°C to + 100°C
Compressive strength	About 30 MPa
Bond/flexural strength	5 MPa
Full dry setting time	8 Hours
Tiles/Granites	All types
Exposure	Swimming pools, spa, sauna, fountain Exterior floors Exterior walls Interior walls & floors

* at temp. = 25-30 °C